

Pigment concentrates based on inorganic pigments

C.I. PB 28

Waterborne, binder-free

Product	Heucodur® Blue 2 R (Heubach)
Water (demin.)	23.6
TEGO® Dispers 750 W	15.0
Defoamer*	1.0
Aerosil® 200 (Evonik)**	0.3
Pigment	60.0
Biocide	0.1
Additive solids on pigment	10 %

* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.

** rheology modifier

Pigment concentrates based on inorganic pigments

C.I. PB 28

Waterborne, universal

Product	Pigment Blue PK 5091 (Ferro)
Water (demin.)	22.1
TEGO® Dispers 651	10.8
TEGO® Dispers 652	1.0
Defoamer*	1.0
Pigment	65.0
Biocide	0.1
Total	100.0
Additive solids on pigment	5 %

* Depending on the pigment and the coating system TEGO® Foamex 8050, TEGO® Foamex 810 or TEGO® Foamex 830 are suitable.